
VERSO

GLAZED PORCELAIN | FLOOR & WALL TILES


PLAIN COLOUR TILES (ABSOLUTE)



VERSO

With distinctive colours like Burnt Orange and Rose, Verso is not afraid to be bold. This is an impressive range that makes a striking statement in any shade. Plus, with all colourways achieving a PTV 36+ slip resistance rating, Verso has the performance credentials to back up its powerful colour palette.

Front Cover Image: Maroon Natural 370x95mm - VRS08N






Roomset Photography






















Colours & Product Codes

V2: Low to Moderate Shade Variation

WHITE BISCUIT N VRSOIN PEI: IV LRV: 65 N VRS07N PEI: IV LRV: 34 BEIGE MAROON N VRS02N PEI: IV LRV: 54 N VRS08N PEI: IV LRV: 16 ROSE BURNT ORANGE N VRS03N PEI: IV LRV: 38 N VRS09N PEI: IV LRV: 21 MINT GREY N VRS04N PEI: IV LRV: 32 N VRSION PEI: IV LRV: 39 SAGE BLUE N VRS05N PEI: IV LRV: 32 N VRSIIN PEI: IV LRV: 15 BLACK GREEN

N VRS06N PEI: IV LRV: 12

N VRS12N PEI: IV LRV: 16



1			

#	Size	Finish	Colour Availability	Thickness	Pieces/Box	Coverage/Box	Weight/Box
I	370x95mm	N Natural	All Colours Shown	9mm	25 Tiles	0.85 m²	17.58 kg

Note: All sizes indicated are metric modular. All dimensions are in millimetres. All sizes shown are nominal. For the most up-to-date availability information, please visit our website. All LRV results are from Johnson Tiles' internal test reports and are to be used for guidance only. LRV: Light Reflectance Value.





Technical Data

Specification

Range	Size	Wall Suitability	Floor Suitability	Wet Barefoot	CSV	Material
Verso	All Sizes Shown	Internal & External	Internal Only	-	V2	Glazed Porcelain [BIa]

Floor Values

Finish	Colour	PTV (4S)	PTV (TRL)	R Value	Wet Ramp	PEI	Traffic
N Natural	All Colours Shown	Dry 36+ Wet 36+	-	-	-	IV	Commercial

Note: Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. Given this, please refer to our website for the most up-to-date information. The slip resistance properties of a surface can only be maintained with the implementation of an effective regular cleaning and maintenance regime. The frequency of cleaning should be determined by the property manager based on the potential level of surface contaminants. The need for an additional regular cleaning and maintenance regime is further heightened when tiles are used for external floor and wet barefoot applications. PTV: Pendulum Test Value.

Physical Properties

Test/Standard	Requirement	Test Result	Test/Standard	Requirement	Test Result
Length / Width EN ISO 10545 - 2	± 0.6% ≤ ± 2mm	Pass	Modulus of Rupture EN ISO 10545 - 4	Min. 35N / mm²	≥ 35N / mm²
Thickness EN ISO 10545 - 2	± 5% ≤ ± 0.5mm	Pass	Thermal Shock EN ISO 10545 - 9	Pass	Pass
Straightness of Side EN ISO 10545 - 2	± 0.5% ≤ ± 1.5mm	Pass	Frost Resistance EN ISO 10545 - 12	Resistant	Resistant
Rectangularity EN ISO 10545 - 2	± 0.5% ≤ ± 2mm	Pass	Chemical Resistance EN ISO 10545 - 13	Min. Class B	Class A
Surface Flatness EN ISO I 0545 - 2	± 0.5% ≤ ± 0.5mm	Pass	Stain Resistance EN ISO 10545 - 14	Min. Class 3	Class 5
Water Absorption EN ISO 10545 - 3	≤ 0.5%	≤ 0.5%	Fire Rating	-	Class AIFL Non Combustible
kg Weight / M²	20.01 kg 9mm thick				

Note: All products are classed as Bia - Glazed Porcelain. All products conform to BS EN 14411.

Important Information

During the manufacturing process of ceramic, vitrified and porcelain tiles, some variation in shade and pattern can occur. Before fixing any tiles; several boxes should be opened and their contents mixed to ensure that size, colour, shade and patterning are acceptable. The tiles shown are quality products and conform to the physical properties listed below.

- All sizes shown are metric modular.
- For specific suitability and fit-for-purpose details please contact our technical helpline.
- Johnson Tiles cannot accept responsibility for any tiles that have been fixed.

 The state of the sta
- \bullet Every effort has been made to ensure the accuracy of the information given.
- Johnson Tiles reserves the right to change specifications and availability without prior notice.
- Nothing in these statements does or will affect the statutory rights of the consumer.

® Johnson Tiles, Johnson, Absolute and Material Lab are registered trademarks and together with Kerastar and product names are the trademarks of H&R Johnson Tiles Limited and licensed to Norcros Group (Holdings) Limited trading as Johnson Tiles. © 2021 Johnson Tiles. All rights reserved.





For more information about Verso or any of our other product ranges simply visit www.johnson-tiles.com | f ♥ ◎ P in ▶

Where To Find Us

Johnson Tiles Harewood Street, Tunstall, Stoke on Trent, Staffordshire, ST6 5JZ

Tel: +44 (0)1782 575 575 Fax: +44 (0)1782 577 377 Email: info@johnson-tiles.com

Samples Enquiries

Tel: +44 (0) I 782 524 043 Fax: +44 (0) I 782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0)1782 524 111 Fax: +44 (0)1782 577 379 Email: techadvice@johnson-tiles.com

JOHNSON-TILES

Since 1901